

Item # P3T-60001 - P3T-60021 (21 colorways)

Sahara Silk

Item # P3T-60001 - P3T-60021, P3T-60320 - P3T-60322 (24 colorways)



Impact



Chemical



Abrasion

PHYSICAL PROPERTIES

| | |
|--------------|-------------------------------------|
| Width | Trim to 48" |
| Packaging | 15-yd rolls |
| Thickness | 0.030 |
| Backing | Heavy Polyester/ Cotton knit |
| Repeat | N/A |
| Installation | Straight hang, Random match |
| Fire Safety | Class "A" rated ASTM E-84; NFPA 286 |



Impact

| | |
|--------------------|-----------------|
| Impact Resistance | ASTM D- 5420-10 |
| Gardner Method | |
| Pattern | In-Lbs |
| Sahara Silk | +100 |



Chemical

| | |
|--|----------------|
| Chemical Resistance | ASTM D- D-1308 |
| Spot test covered 3.1.1 | |
| Cleaning Agents | |
| Tide w/H2O | |
| Virex | |
| Ammonia | |
| Isopropyl Alcohol | |
| Goof Off | |
| Fantastik | |
| Lysol | |
| Hydrogen Peroxide | |
| Bleach | |
| Methyl Ethyl Ketone | |
| Results: No change in P3TEC surface from exposure to these agents. | |

| | |
|-------------|------------|
| Cleaning | ASTM F-793 |
| SECTION 7.5 | |

| | |
|---------------------------|-----------------|
| Abrasion Resistance | ASTM D- 4060-14 |
| Taber Method | |
| Test Spec | |
| CS-10F wheel | |
| 500 gram load @200 cycles | |
| Weight loss: 0.02% | |

ENVIRONMENTAL & HEALTH

| | |
|---------------------|--|
| Indoor Air | Meets California Section 01350 |
| Fungal Resistant | ASTM G-21 |
| Bacterial Resistant | ASTM G-22 |
| HPD | third-party classified |
| EPD | third-party certified |
| NSF/ANSI 342 | third-party certified, ask distributor for details |

| | | |
|---|--|---|
| Impact | Chemical | Abrasion |
| Impact Resistance ASTM D- 5420-10 Gardner Method Pattern Sahara Silk | Chemical Resistance ASTM D- D-1308 Spot test covered 3.1.1 Cleaning Agents Tide w/H2O Virex Ammonia Isopropyl Alcohol Goof Off Fantastik Lysol Hydrogen Peroxide Bleach Methyl Ethyl Ketone Results: No change in P3TEC surface from exposure to these agents. | Cleaning ASTM F-793 SECTION 7.5 Staining Agents Grape Juice Mustard Black Sharpie Ink Pen Betadine Shoe Polish Lipstick Black Rubber Brake Fluid Spray Paint Results: Each staining agent above was wiped clean with at least one listed cleaning agent. Best stain removal results can be achieved by use of progressively strong, non-abrasive cleaners, and which can be supplemented by use of a soft bristle brush. |

OTHER

5 year warranty against manufacturing defects.

Accessories: Coordinating corner guards and Type II wallcovering (on selected colorways) available.

Installs with techniques similar to Type II vinyl wallcovering, including seaming with overlap and double-cut process.

See full installation instructions from distributor.

Sold in 15-yd coreless rolls, one per shipping box (approximately 42 lbs)